



# ICAT INDUSTRIES

## FC210 Ambercoat Product Data Sheet

### Description:

ICAT-FC-210 Ambercoat is an extensively tested (CSA Z245.20) external pipeline coating. The FC-210 is a 100% solids fast set external polyurethane pipeline coating. Based on the FC 210's excellent adhesion and abrasion characteristics, it's extremely quick turnaround time, along with its cold temperature curing characteristics, makes it the "go to" coating for the new construction and rehabilitation of pipelines, valves and bends as well as "winter dig" programs for over 20 years.

### Uses:

FC210 is a two component, 100% solids polyurethane coating system, which may be applied directly to steel.

### Features:

- Quick set / fast turn around times
- Low temperature cure
- High build – up to 80 mils in a single coat
- Grey in colour
- Finish: Gloss
- Pipeline: New Construction, Rehabilitation & Coating Repair
- 100% solids content - VOC Compliant
- Excellent Adhesion and resistance to Cathodic Disbondment
- Provides monolithic membrane protection to the substrate
- Quick return to service
- Available in 200L drums (800L kits), 18L pails (72L kits) and brush grade kits of various sizes

### Application:

#### *Surface Prep:*

Surfaces must be clean and dry. Remove all contaminants such as dust, dirt and oils. SSPC SP 10 / NACE 2 Near White with a minimum jagged profile of 3.0 utilizing a suitable abrasive such as nickel slag, aluminum oxide & garnet.

#### *Spray:*

FC-210 Ambercoat shall be applied to blasted steel surfaces using plural component spray equipment. The ratio of the pump shall be 3 parts A (Base) to 1 part B (Curing Agent).

FC-210 Ambercoat Base (Part A) shall be preheated to a temperature of no less than 35°C/95°F while being agitated. A transfer pump with a fluid-to-air ratio of no less than 10:1 is recommended to feed the plural component pump. Inline heaters shall be used on the Base (Part A) side to raise the temperature to 60°C/140°F upon application.



# ICAT INDUSTRIES

FC-210 Ambercoat Curing Agent (Part B) shall be transferred to the plural component pump with a minimum 5:1 fluid-to-air pump and should be at a minimum temperature of 15°C/60°F. Agitation is not required unless preheating is done to attain this temperature.

The hose bundle leaving the plural component pump shall be heat traced and insulated to maintain the material temperature. The base (Part A) line shall be 3/8 inch ID and have a minimum operating strength of 5000 psi. The curing agent (Part B) shall be 1/4 inch ID and have a minimum operating strength of 6000 psi. A maximum length of 50 metres (150 feet) shall be used.

The mixing block shall have a material shut off valve prior to entry and must have a solvent flush attachment that will allow the mixing block and whip hose to be flushed of material.

The whip hose shall be 1/4 inch ID and no more than 5 metres (15 feet) in length. The gun shall be a high pressure airless spray gun with a minimum pressure rating of 3000 psi.

## ***Brush & Roll:***

Combine pre-measured base material (Part A) with pre-measured curing agent (Part B) and mix thoroughly using a drill with a mixing attachment.

Once mixed, apply to abrasive blasted steel surface using a brush/roller/trowel to attain an even coat.

## ***Repair Procedure:*** Repairs to coating shall be performed in one of 2 ways:

Small Area Repairs – Coating repairs less than 152mm/6-inch diameter can be abraded with 80 grit carborundum cloth, file, MBX® Bristle Blaster® or abrasive blasting to roughen the coating surface for repair. The entire area may then be coated by brush or roller using FC210 Ambercoat Brush Grade material.

Large Area Repairs – areas larger than those above are recommended to be prepared in the same manner and then repaired by spray application.

## ***Testing:***

Holiday testing may be performed when the coating is tack free and has a shore D hardness of at least 60. Destructive testing should be performed after the coating has had at least 24 hours at 25°C to cure.

**\*During the blasting operation and until the final coating procedure has been finished, the temperature of the steel shall not be less than 3°C/5°F above the dew point.**



# ICAT INDUSTRIES

Properties	Value
<b>Solids Content</b>	100%
<b>Mixed Material</b>	
• Colour	Grey
• Specific Gravity	1.48 combined A and B
<b>Mixing Ratio</b>	3:1 Ratio
<b>Full Cure Time (25°C)*</b>	24 hours
<b>Estimated time/temperature for cure</b>	
• (15°C/60°F)	2 hours
• (4°C/40°F)	4 hours
• (0°C/32°F)	6 hours
• (-5°C/23°F)	14 hour
<b>Theoretical Coverage</b>	1 sq. m/liter at 1 mm thickness
<b>Thickness</b>	
• Recommended	30/80 mils (750/1000 microns)
<b>Holiday Detection:</b>	Standard Corrosion Protection: 3,000DCV Abrasion Resistance Protection: 5,000DCV
<b>Cathodic Disbondment Test</b>	
• 24 hour @ 65°C	2.1 mm
• 28 days @ 20°C	3.5 mm
• 28 days @ 40°C (max temp)	7.3 mm
<b>Hardness</b>	Shore "D" 75
<b>Impact Resistant @ 0°C</b>	7 Joules
<b>Tabor Abrasion</b>	
CS 17 wheel 1000 cycles 1 kg load	42 mg
<b>0.75°@-30°C Flexibility</b>	pass
<b>Adhesion to steel</b>	rating 1
<b>Adhesion to existing coating</b>	rating 1
<b>28 day Adhesion to Steel @ 75°C</b>	rating 1
<b>28 day adhesion to Existing Coating @ 95°C</b>	rating 2
• Substrate	23°F to 212°F (-5°C to 100°C)
<b>Gouge Resistance</b>	17 mils

\* For additional data, including curing schedules, please contact the product manufacturer.

**Storage:** Minimum 24 months when stored in original sealed containers @ 34°F (1°C) to 113°F (45°C). When temperatures are below 32°F (0°C) the catalyst may partially crystallize. If so, slowly bring part B to temperature to 70°F (21°C) and mix till product is a homogeneous. **Cleaning:** use suitable non-water containing solvent such as MEBK, Acetone, Xylene (contact manufacturer if unknown) to clean equipment.

**Health and Safety:** Always wear protective gear and avoid contact with skin. Do not ingest. See material safety data sheet for further information.

**Packaging:** 18L Pails, 200L drums and premeasured brush & repair kits available upon request

All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties, express or implied: Sellers and manufacturers only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use or inability to use the product. Before using, user shall determine the suitability of the product for the intended use, and user assumes all risk and liability whatsoever in connection therewith. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of seller and manufacturer.